

Zhejiang Qianxiong Special Fibre Co.,Ltd

No 366 Kechuang Road, Economic Development Zone, Yongkang City, Zhejiang Province, China

Email: info@chinaqianxi.com

Technical data				
Specification	Fibre number	Breaking tenacity	Breaking modulus	Breaking elongation
	dtex	cN/dtex	cN/dtex	%
QXL-10D	11	≥40	≥1500	≤3.5
QXL-15D	17	≥40	≥1500	≤3.5
QXL-20D	22	≥40	≥1500	≤3.5
QXL-25D	28	≥40	≥1500	≤3.5
QXL-30D	33	≥40	≥1500	≤3.5
QXL-40D	44	≥40	≥1500	≤3.5
QXL-50D	55	≥40	≥1500	≤3.5
QXL-75D	83	≥38	≥1400	≤3.5
QXL-100D	111	≥35	≥1350	≤3.0
QXL-125D	139	≥35	≥1350	≤3.0
QXL-150D	165	≥34	≥1300	≤3.0
QXL-175D	193	≥33	≥1250	≤3.0
QXL-200D	222	≥33	≥1250	≤3.0
QXL-225D	248	≥33	≥1250	≤3.0
QXL-250D	275	≥33	≥1250	≤3.0
QXL-300D	333	≥32	≥1200	≤3.0
QXL-350D	389	≥32	≥1200	≤3.0
QXL-400D	444	≥32	≥1200	≤3.0
QXL-500D	555	≥32	≥1200	≤3.0
QXL-600D	667	≥32	≥1200	≤3.0
QXL-700D	777	≥30	≥1100	≤3.5
QXL-800D	889	≥30	≥1100	≤3.5
QXL-1000D	1111	≥30	≥1100	≤3.5
QXL-1200D	1333	≥30	≥1100	≤3.5
QXL-1400D	1554	≥30	≥1100	≤3.5
QXL-1600D	1778	≥30	≥1100	≤3.5
QXLG-800D	889	≥34	≥1200	≤3.5
QXLG-1200D	1333	≥34	≥1200	≤3.5
QXLG-1600D	1778	≥34	≥1200	≤3.5